



NEVASTANE HD2T

DESCRIPTION

Extreme pressure aluminum complex grease, suitable for incidental food contact.



No MOAH* (mineral Oil Aromatic Hydrocarbons) in our grease

* Test realized in external laboratory

SPECIFICATIONS

- ISO 6743-9 : L-XBDHB2
- DIN 51502: KP2N-20.

APPLICATIONS

- **NEVASTANE HD2T** is an extreme pressure and adhesive multipurpose grease based on aluminum complex soap with PTFE.
- **NEVASTANE HD2T** is recommended for the lubrication of numerous applications operating under severe conditions (especially in the presence of water) in the food and beverage industry: loaded bearings, seamers, bottling machines...
- **NEVASTANE HD2T** has a wide operating temperature range: -20°C to +150°C.

ADVANTAGES

- **NEVASTANE HD2T** is recommended for use where incidental contact with food may occur. Using maintenance lubricants which have been registered H1 with NSF minimizes your critical control points as required by HACCP.
- Exceptional adhesion to metal surfaces.
- Excellent resistance to water washout.
- Very good protection against corrosion.
- Superior extreme pressure characteristics.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.
A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded at ms-sds.totalenergies.com

RECOMMENDATIONS

- Shake well before use
- Hold upright and spray from a distance of about 20 cm
- Shelf life: 3 years from date of manufacture (unopened).
- Store between 0°C and 40°C
- Do not spray on a naked flame or any incandescent material.

APPROVALS

- The formulation of **NEVASTANE HD2T** complies with the FDA chapter 21 CFR, 178.3570.
- **NEVASTANE HD2T** is NSF H1 registered: No 137924.
- **NEVASTANE HD2T** is Kosher, Halal and ISO 21469 certified.

TYPICAL CHARACTERISTICS

TYPICAL CHARACTERISTICS	METHODS	UNITS	NEVASTANE HD2T
Soap/thickener	-	-	Aluminum complex
Color	Visual	-	Beige
Appearance	Visual	-	Smooth, homogeneous and slightly tacky
NLGI grade	ASTM D 217	grade	2
Operating temperature range	-	°C	from -20°C to +150°C
Penetration at 25 °C	ASTM D 217	0.1 mm	265 - 295
Four ball - weld load	ASTM D 2596	kgf	315
Copper corrosion	ASTM D 4048	-	1a
Dropping point	IP 396	°C	> 240
Water spray off	ASTM D 4049	%	12
Base oil type	-	-	White oil (with polymers)
Kinematic viscosity at 40 °C	ISO 3104	mm ² /s	150

Above characteristics are mean values given as an information.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded at ms-sds.totalenergies.com