



# Nevastane XS 220 Spray

## DESCRIPTION

- Food-grade, EP, calcium sulfonate complex grease.
- Nevastane XS 220 Spray is formulated without MOAH, ensuring food safety in compliance with Commission Recommendation (EU) 2017/84.



## APPLICATIONS

- Nevastane XS 220 Spray is an extreme pressure grease dedicated to lubrication in the food industry, under severe conditions: water, high load, high temperature, dust...
- Nevastane XS 220 Spray is recommended for the lubrication of pelleting presses (KAHL, Promill Stolz, CPM, UMT) in feed and sugar industries, paper mill.
- Shake the aerosol before use – Spray from a 15-25 cm distance

## CAUTION

Due to the container and the presence of solvents:

- Keep away from heat, sparks, and flames.
- Do not expose to heat and temperatures exceeding 50°C.
- Even when empty, do not puncture or incinerate the container.

Keep away from daylight, dust, and humidity.

Shelf life: 2 years from date of manufacture.

## ADVANTAGES

- Increase of the equipment lifespan while reducing contamination problems as required by the Hazard Analysis and Critical Control Point System (HACCP).
- Excellent mechanical and thermal stability (high dropping point).
- Remarkable load resistance thanks to its naturally high extreme pressure and anti-wear properties.
- Outstanding water and steam resistance and excellent food acids/alkalis resistance. No significant loss of consistency is observed even with high amounts of water entering the grease.

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded at [www.quick-fds.com](http://www.quick-fds.com).

- Excellent anti-oxidation and anti-corrosion properties, even in the presence of salt water.
- Non-flammable propellant gas: CO2

## TYPICAL CHARACTERISTICS

PROPERTIES	Nevastane XS 220 Spray	UNITS	STANDARDS
Thickening agent	Calcium Sulfonate Complex	-	-
Color	Light beige	-	Visual
Appearance	Smooth	-	Visual
Penetration at 25°C	280 – 310	0.1mm	ASTM D 217
NLGI grade	1.5	NLGI Grade	ASTM D 217
Operating temperature range	From -35 to 160	°C	-
Four ball – weld load	480	daN	DIN 51350/4
Anti-rust performance SKF-EMCOR	0 - 0	rating	ISO 11007
Dropping point	>300	°C	ISO 2176
Base oil type	White oil/PAO (with polymers)	-	-
Kinematic viscosity at 40 °C	220	mm <sup>2</sup> /s	ISO 3104

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk.

A material safety data sheet conforming to the regulations in use in the E.C. can be obtained from your local commercial adviser or downloaded at [www.quick-fds.com](http://www.quick-fds.com).